


SHA PORTLAND CEMENT CONCRETE MIXTURE

Mix No.	28 Day Specified Design Compressive Strength (PSI)	Min. Cement Factor (LB/YD ³)	Coarse Aggregate AASHTO M43 Size	Max. Water Cement Ratio	Slump (In)
1	2500	455	57 or 67	0.55	2-5
2	3000	530	57 or 67	0.50	2-5
3	3500	580	57 or 67	0.50	2-5

Mix No.	Total Air Content (%)	Concrete Temperature (F)
1	5-8	70 ± 20
2	5-8	70 ± 20
3	5-8	70 ± 20

Note:

1. State Certified Concrete Manufacturer.

APPROVAL	REVISED	TOWN OF EASTON AND EASTON UTILITIES STANDARD DETAILS SHA PORTLAND CEMENT CONCRETE MIXTURE
 EU MANAGER OF ENGINEERING DATE	AUG 1, 94	
	MAR 1, 98	
ISSUED: <u>MAY 1, 1986</u>	STANDARD NO. G-3.00	